

Test Report

Testing institute : Product Technology Service (Ningbo) Co., Ltd.
5-7F, 59#, Huayu Road, Yinzhou District, Ningbo, Zhejiang

Applicant : NINGBO YUBO IMPORT AND EXPORT CO.,LTD.
NO.150, HUIJIANG ROAD YINZHOU DISTRICT NINGBO(1704-A CHENGNAN BUSINESS BUILDING)

Product name : PILL ORGANIZER

Model No. : G142880/G14382/G14564T/G14378T

Sample Description : /

Material : /

Sample receive date : Aug.17,2022

Completes date : Aug.25,2022

Test specification(s)	Conclusion
1. US FDA 21 CFR 177.1520(a)(1)(i) and (c)1.1a The test compliance with the Food and Drug Administration Regulations for Polypropylene(PP)(a)(1)(i) used in contact with food.	
1.1-Density at 23°C	Pass
1.2-Melting Point	Pass
1.3-Extractable fraction in n-hexane at reflux temperature	Pass
1.4-Soluble fraction in xylene at 25°C	Pass
2.Total Lead ----California Proposition 65	Pass
3.Total Cadmium ----California Proposition 65	Pass
4.Phtalates ----California Proposition 65	Pass

Signed for and on behalf of
Product Technology Service (Ningbo) Co., Ltd.

Davy Wei


Authorizer: Davy Wei

The test results exclusively refer to the samples examined. The test report is only used for scientific research, teaching or internal quality control. This report shall not be reproduced except in full without written approval and does not authorize the use of Product Technology Service (Ningbo) Co., Ltd. label. The report is invalid without signature and seal of Product Technology Service (Ningbo) Co., Ltd.

Product name

No.	Name	Part No.	Part Name
1	PILL ORGANIZER	1-1	Medicine box: white rectangular plastic
		1-2	Yellow plastic cover

1. US FDA 21 CFR 177.1520: Olefin polymers requirements

Product name: 1-1.Medicine box: white rectangular plastic				
Parameter	Unit	Polypropylene(PP) (a)(1)(i) Limit	Detection Limit	Result
Melting Point *	°C	160-180	--	171.9
Extractable fraction in n-hexane at reflux temperature	w/w %	6.4 max.	1.0	1.1
Soluble fraction in xylene at 25°C	w/w %	9.8 max.	1.0	3.0
Conclusion				Pass
Density at 23°C	g/cm ³	0.880–0.913	--	0.905
Conclusion				Pass

Note:

- 1) ND=Not Detected(<Detection Limit)
- 2) "--"=Not Regulated
- 3) "*" =The test is carried out by external laboratory assessed as competent

2.Test specification : Total Lead ----California Proposition 65
Test method : CPSC-CH-E1002-08.3
Requirement : California Proposition 65

Test Product No.	Testing element	Pb	Conclusion
	Detection Limit[mg/kg]	10.0	
	Limit [mg/kg]	100	
1-2	--	ND	Pass

ND = Not Detected (< Detection Limit)

Main test instruments used for this method:

Instrument	Manufactory	Model / Type
ICP-OES	PerkinElmer	Optima 5300 DV

3.Test specification : Total Cadmium ----California Proposition 65

Test method : US EPA 3052:1996 and US EPA 6010D:2018

Requirement : California Proposition 65

Test Product No.	Testing element	Cd	Conclusion
	Detection Limit[mg/kg]	10.0	
	Limit [mg/kg]	100	
1-2	--	ND	Pass

ND = Not Detected (< Detection Limit)

Main test instruments used for this method:

Instrument	Manufactory	Model / Type
ICP-OES	PerkinElmer	Optima 5300 DV

4.Test specification : Phthalates ----California Proposition 65

Test method : CPSC-CH-C1001-09.4
Standard Operating Procedure for Determination of Phthalates

Requirement : California Proposition 65

Test Product No.	CAS No.	Detection	Limit	1-2
Dibutyl phthalate (DBP)	84-74-2	0.005%	0.1%	ND
Butyl benzyl phthalate (BBP)	85-68-7	0.005%	0.1%	ND
Di-2-ethylhexyl phthalate (DEHP)	117-81-7	0.005%	0.1%	ND
Di-iso-decyl phthalate (DIDP)	26761-40-0/ 68515-49-1	0.005%	0.1%	ND
Di-n-hexyl phthalate(DnHP)	84-75-3	0.005%	0.1%	ND
Di-iso-nonyl phthalate (DINP)	28553-12-0/ 68515-48-0	0.005%	0.1%	ND
Conclusion				Pass

ND = Not Detected (< Detection Limit)

Main test instruments used for this method:

Instrument	Manufactory	Model / Type
GC-MS	Agilent Technologies	GC (7890)-MS (5975C)

Sample photo(s), see annex 1

---End---

ANNEX 1

Sample photo(s), consists of 1 page



PILL ORGANIZER