



TEST REPORT

Test information

Applicant	:	NINGBO SHIMAOTONG INTERNATIONAL CO.,LTD.
Address	:	Room 1203, Building 004, 495 Jiangdong North Road, Yinzhou District, Ningbo City, Zhejiang Province.
Sample Description	:	Medicine box.
PO#	:	Not provided.
Style #	:	Not provided.
Country of origin	:	China.
Export to	:	Not provided.
Buyer	:	Not provided.
Receiving Date	:	June 21, 2022.
Test period	:	June 21, 2022.~June 25, 2022.
Amended date	:	June 28, 2022.
Test Requested	:	Tests requested in accordance to client requirement.

<u>TEST ITEMS</u>	<u>CONCLUSION</u>
Extractable fraction in n-hexane – US FDA 21 CFR 177.1520	PASS
Total Lead(Pb) Content - California Proposition 65- Superior Court of California- County of San Francisco Case No. CGC-05-440811/Alameda Case No. HG-04-183355	PASS
Total Cadmium(Cd) Content - California Proposition 65- Superior Court of California- County of Alameda Case No. RG 10-514803.	PASS
Phthalates Content test - California Proposition 65	PASS


This report replaces the original report: RTS220621P2941FD, The original report was voided.

Signed for and on behalf of
RTS TEST CO., LTD. (Zhejiang)



BINBIN ZOU

Approved signatory



Scan to follow us



Scan for authenticity

Zhejiang RTS Test Co., LTD.

Phone: +86(0)579-85640080

Email: ruiyi-8@zi-rt.com

<http://www.irtslab.com>

浙江省义乌市稠江街道英才创业园B区7幢2-4层,
2-4/f, Building 7, Block B, Ying cai Business Park,
Choujiang Street, Yiwu, Zhejiang.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request. Attention is drawn to the limitation of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test report refer only to the sample(s) tested unless otherwise stated. This test report shall not be reproduced, except in full, without written approval of the Company. If in doubt, please write an email. * This item is beyond CNAS permitting capacity list and proceed by outsourcing labs.

Sample image:



**Test result:****A.*Extractable fraction in n-hexane – US FDA 21 CFR 177.1520:(Unit: w/w %)**

Test method: With reference to US FDA 21 CFR 177.1520.

Test Number	Item/ component description(s)	Material (claimed by the client)
A1	White PP	PP

Simulant Used	Time	Temp	Detection limit	Test result A1	Maximum permissible Limit
Extractable fraction in n-hexane at reflux temperature , w/w %	2h	reflux temperature	0.5	N.D.	6.4

Note:

- 1)N.D= Not detected, less than Detection limit.
- 2)%(w/w) = percentage of weight by weight.
- 3) Maximum permissible Limit is reference to 21 CFR 177.1520(c) 1.1a.

B. Total Lead(Pb) contents: (Unit: mg/kg)

California Proposition 65- Superior Court of California- County of San Francisco Case No. CGC-05-440811/Alameda Case No. HG-04-183355

Test method:

Metal - CPSC-CH-E1001-08.3., Nonmetal - CPSC-CH-E1002-08.3.,

Was analyzed by flame atomic absorption spectrometry (AAS) or inductively coupled plasma spectrometer (ICP-OES).

Test Number	Item/ component description(s)
A2	Inner black plastic & white plastic & transparent cover

Test item	Test Number	MDL	Test Result	Maximum permissible limit	Conclusion
Lead (Pb)	A2▲	5	N.D.	200	PASS

Note:

- 1) MDL=Method Detection Limit.
- 2) N.D. = not detected, less than MDL.
- 3) Product shall not exceed 200 ppm (0.02%) total lead content..
- 4)“▲” = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.

Remark:Zhejiang RTS Test Co.,Ltd. is the US (CPSC) Accredited Third Party Testing Laboratory, [LAB ID: 1422](#), Shall refer to:<https://www.cpsc.gov/cgi-bin/LabSearch/ViewDetail.aspx?ReqId=7%2bFdY2oZNSUVU5mVbl6jQA%3d%3d&LabId=CJaa18d5DKIPqgie8zcyw%3d%3d>**Zhejiang RTS Test Co., LTD.**

Phone: +86(0)579-85640080

Email: ruiyi-8@zj-rt.com<http://www.irtslab.com>浙江省义乌市稠江街道英才创业园B区7幢2-4层,
2-4/f, Building 7, Block B, Ying cai Business Park,
Choujiang Street, Yiwu, Zhejiang.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request. Attention is drawn to the limitation of liability ,indemnification and jurisdictional policies defined therein .The results shown in this Test report refer only to the sample(s) tested unless otherwise stated This test report shall not be reproduced ,except in full, without written approval of the Company. If in doubt, please write an email.

**C. Total Cadmium(Cd) content:** (Unit: mg/kg)

California Proposition 65- Superior Court of California- County of Alameda Case No. RG 10-514803

Test method: RTS-ZY-008 As per Metal - CPSC-CH-E1001-08.3; Nonmetal - CPSC-CH-E1002-08.3; Surface coating - CPSC-CH-E1003-09.1, Was analyzed by flame atomic absorption spectrometry(AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Test Number	Item/ component description(S)
A2	Inner black plastic & white plastic & transparent cover

Test item	Test Number	MDL	Test Result	Maximum permissible limit	Conclusion
Cadmium (Cd)	A2▲	5	N.D.	300	PASS

Note:

- 1) MDL=Method Detection Limit.
- 2) N.D. = not detected, less than MDL.
- 3) Product shall not exceed 300 ppm (0.030%) total cadmium content.
- 4)“▲” = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.

**D. Phthalates Content test - California proposition 65:** (Unit: mg/kg)

Test method: CPSC-CH-C1001-09.4, was analyzed by Gas Chromatograph-Mass Spectrometer (GC-MS).

Test Number	Item/ component description(s)			
A2	Inner black plastic & white plastic & transparent cover			
Test Item(s)	CAS No.	Results A2▲	MDL	Limit value
Dibutyl Phthalate(DBP)	84-74-2	N.D.	50	1000
Benzylbutyl Phthalate(BBP)	85-68-7	N.D.	50	1000
Bis-(2-ethylhexyl)Phthalate(DEHP)	117-81-7	N.D.	50	1000
Diisodecyl Phthalate(DIDP)	26761-40-0	N.D.	50	1000
Di-iso-nonyl Phthalate(DINP)	28553-12-0	N.D.	50	1000
Di-n-hexyl phthalate (DNHP)	84-75-3	N.D.	50	1000
Conclusion:	-	PASS	-	-

Note:

- 1) N.D. = not detected, less than MDL.
- 2) MDL = Method Detection Limit.
- 3) "▲" = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.

----- End of Report -----

Zhejiang RTS Test Co., LTD.

Phone: +86(0)579-85640080
Email: ruiyi-@zi-rt.com
<http://www.irtslab.com>
浙江省义乌市稠江街道英才创业园B区7幢2-4层.
2-4/f, Building 7, Block B, Ying cai Business Park,
Choujiang Street, Yiwu, Zhejiang.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request. Attention is drawn to the limitation of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test report refer only to the sample(s) tested unless otherwise stated. This test report shall not be reproduced, except in full, without written approval of the Company. If in doubt, please write an email.