

TEST REPORT

Report No.: SZ3220916-42233E

Date: September 22, 2022

Page 1 of 6

FOURSTAR GROUP

UNIT A,8/F KAISER ESTATE PHASE 1, 41 MAN YUE STREET, HUNG HOM KOWLOON, HONGKONG

Report on the submitted samples said to be:

Sample Description:	TUMBLER PLASTIC TIKI FACES
Style/Item No.:	61171145
Country of Origin:	China
Country of Destination:	USA
Manufacturer:	NINGBO MASCUBE IMP. & EXP. CORP.
Supplier:	FOURSTAR GROUP
Buyer:	REGENT
Sample Receiving Date:	September 19,2022
Testing Period:	September 19,2022 - September 22,2022
Result:	Please refer to next page(s).

Signed for and on behalf of

BACL

Queenie Lee

Checked by: _____
Queenie Lee

Lance Lee

Approved by: _____
Lance Lee

TEST REPORT

Report No.: **SZ3220916-42233E**

Date: September 22, 2022

Page 2 of 6

Summary of Test Result:

TEST REQUEST

CONCLUSION

A. FDA food Contact Article test

A.1 Polystyrene in accordance with 21 CFR 177.1640

Pass

B. US California Proposition 65. on Bisphenol A (BPA) content in the components of submitted sample as the requirement of client

Pass*¹

Pass*¹ = Meet the requirement of Client.

TEST REPORT

Report No.: SZ3220916-42233E

Date: September 22, 2022

Page 3 of 6

Result:

Tested part(s):

- (1) Pink PS(body of cup)
- (2) Purple PS(body of cup)
- (3) Blue PS(body of cup)
- (4) Light green PS(body of cup)

TEST REPORT

Report No.: SZ3220916-42233E

Date: September 22, 2022

Page 4 of 6

A. FDA food Contact Article test

A.1 Polystyrene in accordance with 21 CFR 177.1640

Test method: 21 CFR 177.1640

Item	Unit	MDL	Result				Limit
			(1)	(2)	(3)	(4)	
Residual styrene monomer	%	0.002	0.061	0.066	0.102	0.043	1
Conclusion	/	/	Pass	Pass	Pass	Pass	/

B. US California Proposition 65. on Bisphenol A (BPA) content in the components of submitted sample as the requirement of client

Test method: solvent extraction and Liquid Chromatographic / Tandem Mass spectrometer (LC/MS/MS) analysis

Item	Unit	MDL	Result	Client's Limit
			(1)	
Bisphenol A(BPA)	mg/kg	0.1	N.D.	0.1
Conclusion	/	/	Pass	/

Note:

- N.D.= Not Detected or less than MDL

- MDL = Method Detection Limit


TEST REPORT

Report No.: SZ3220916-42233E

Date: September 22, 2022

Page 5 of 6

Photograph of Sample



BACL authenticate the photo on original report only

TEST REPORT

Report No.: SZ3220916-42233E

Date: September 22, 2022

Page 6 of 6

Statement:

- 1.This report cannot be reproduced except in full, without prior written approval of the Company.
- 2.Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
- 3.This report is valid only with a valid digital signature. The digital signature may be available only under the Adobe software above version 7.0.
- 4.Otherwise required by the applicant or Product Regulations, Decision Rule in this report did not consider the uncertainty.
- 5.The information which provided by the applicant, such as sample description, sample name, material component, style/item No. , P.O. No. , manufacturer, age phase, the laboratory is not responsible for its authenticity and this information can affect the validity of the result in the test report.
- 6.The test samples were in good condition before testing.

*** End of Report ***