

Report No.: RTS220607X0805HL Date: 2022-06-10 Page 1 of 5

TEST REPORT

| | | Test information |
|-------------------|---|--|
| Applicant | : | Ningbo Home-Dollar Imp.& Exp.Corp. |
| Address | : | 69 Guangyuan Road, Jiangbei District, Ningbo,China. |
| Sample Name | : | SINK MAT. |
| PO# | : | Not provided. |
| Style# | : | G25649. |
| Supplier | : | Ningbo Home-Dollar Imp.& Exp.Corp. |
| Country of origin | : | China. |
| Export to | : | USA. |
| Buyer | : | REGENT PRODUCTS CORP. |
| Receiving Date | : | June 07, 2022. |
| Test period | : | June 07, 2022.∼June 10, 2022. |
| Test Requested | : | Tests requested in accordance to client requirement. |

| TEST ITEMS | CONCLUSION |
|---|------------|
| Total Lead(Pb) Content - California Proposition 65- Superior Court of California- County of Santa Clara | PASS |
| Case No. 112CV231165. | FAGG |
| Total Cadmium(Cd) Content - California Proposition 65- Superior Court of California- County of Alameda | PASS |
| Case No. RG 10-514803. | PASS |
| Phthalates Content test- Client's requirement | PASS |

Signed for and on behalf of

CHANGBIAO YU

Approved signatory



Report No.: RTS220607X0805HL Date: 2022-06-10 Page 2 of 5

Sample image:





Report No.: RTS220607X0805HL Date: 2022-06-10 Page 3 of 5

Test result:

A. Total Lead(Pb) content: (Unit: mg/kg)

California Proposition 65- Superior Court of California- County of Santa Clara Case No. 112CV231165.

Test method: As per Metal - CPSC-CH-E1001.08.3; Nonmetal - CPSC-CH-E1002.08.3; Surface coating -

CPSC-CH-E1003.09.1, Was analyzed by flame atomic absorption spectrometry (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

| Test Number | Item/ component description(s) | |
|-------------|----------------------------------|--|
| A1 | Plastic mat (black & red & grey) | |

| Test item | Test Number | MDL | Test Result | Maximum permissible limit | Conclusion |
|-----------|-------------|-----|-------------|---------------------------|------------|
| Lead | A1 ▲ | 5 | N.D. | 100 | PASS |
| (Pb) | AI A | 5 | N.D. | 100 | PASS |

Note:

- 1) MDL=Method Detection Limit.
- 2) N.D. = not detected, less than MDL.
- 3) Products shall not exceed 100 ppm (0.01 %) total lead content.
- 4) Products shall produce a result of 1.0 micrograms or less lead in Ghost WipeTM test
- 5)"▲" = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.

Remark:



Report No.: RTS220607X0805HL Date: 2022-06-10 Page 4 of 5

B. Total Cadmium(Cd) content: (Unit: mg/kg)

California Proposition 65- Superior Court of California- County of Alameda Case No. RG 10-514803

Test method: RTS-ZY-008 As per Metal - CPSC-CH-E1001-08.3; Nonmetal - CPSC-CH-E1002-08.3; Surface coating - CPSC-CH-E1003-09.1, Was analyzed by flame atomic absorption spectrometry(AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

| Test Number | Item/ component description(S) |
|-------------|----------------------------------|
| A1 | Plastic mat (black & red & grey) |

| Test item | Test Number | MDL | Test Result | Maximum permissible limit | Conclusion |
|-----------|-------------|-----|-------------|---------------------------|------------|
| Cadmium | A1 ▲ | 5 | N.D. | 300 | PASS |
| (Cd) | AI A | | N.D. | 300 | 1 700 |

Note:

- 1) MDL=Method Detection Limit.
- 2) N.D. = not detected, less than MDL.
- 3) Product shall not exceed 300 ppm (0.030%) total cadmium content.
- 4)"▲" = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.



Date: 2022-06-10 Report No.: RTS220607X0805HL Page 5 of 5

C.Phthalates Content Test: (Unit: mg/kg)

Test method: With reference to CPSC-CH-C1001-09.4, was analyzed by Gas Chromatograph-Mass Spectrometer (GC-MS).

| Test Number | Item/ component description(s) | |
|-------------|----------------------------------|--|
| A1 | Plastic mat (black & red & grey) | |

| Test Item(s) | CAS No. | Results A1 ▲ | MDL | Client's Limit |
|-----------------------------------|------------|------------------------|-----|----------------|
| Dibutyl Phthalate(DBP) | 84-74-2 | N.D. | 50 | 1000 |
| Benzylbutyl Phthalate(BBP) | 85-68-7 | N.D. | 50 | 1000 |
| Bis-(2-ethylhexyl)Phthalate(DEHP) | 117-81-7 | N.D. | 50 | 1000 |
| Di-iso-nonyl Phthalate(DINP) | 28553-12-0 | N.D. | 50 | 1000 |
| Di-iso-decylphthalate(DIDP) | 26761-40-0 | N.D. | 50 | 1000 |
| Di-n-hexyl phthalate(DNHP) | 84-75-3 | N.D. | 50 | 1000 |
| Conclusion | - | PASS | - | - |

Note:

- 1) N.D. = not detected, less than MDL.
- 2) MDL = Method Detection Limit.
- 3)"▲" = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.

| End of | Report | |
|------------|--------|--|