

## Test Report

Testing institute : Product Technology Service (Ningbo) Co., Ltd.  
5-7F, 59#, Huayu Road, Yinzhou District, Ningbo, Zhejiang

Applicant : NINGBO YUBO IMPORT AND EXPORT CO.,LTD.  
NO.150, HUIJIANG ROAD YINZHOU DISTRICT NINGBO(1704-A CHENGNAN  
BUSINESS BUILDING)

Product name : SILICONE SPATULA/SINK STRAINER

Model No. : G470070/G25738/G25739/G25803T

Sample Description : /

Material : /

Sample receive date : Oct.11,2022

Completes date : Oct.17,2022

Test specification(s)	Conclusion
1.Total Lead ----California Proposition 65	Pass
2.Total Cadmium ----California Proposition 65	Pass
3.Phtalates ----California Proposition 65	Pass
4. US FDA 21 CFR 177.2600: Rubber articles intended for repeated use(e)&(f)	
(e)Rubber articles intended for repeated use in contact with aqueous food;	Pass
(f)Rubber articles intended for repeated use in contact with fatty foods.	Pass

Signed for and on behalf of  
Product Technology Service (Ningbo) Co., Ltd.



Authorizer: Davy Wei

The test results exclusively refer to the samples examined. The test report is only used for scientific research, teaching or internal quality control. This report shall not be reproduced except in full without written approval and does not authorize the use of Product Technology Service (Ningbo) Co., Ltd. label. The report is invalid without signature and seal of Product Technology Service (Ningbo) Co., Ltd.

Product name

No.	Name	Part No.	Part Name
1	SILICONE SPATULA/ SINK STRAINER	1-1	White silica gel

1.Test specification : Total Lead ----California Proposition 65

Test method : CPSC-CH-E1002-08.3

Requirement : California Proposition 65

Test Product No.	Testing element	Pb	Conclusion
	Detection Limit[mg/kg]	10.0	
	Limit [mg/kg]	100	
1-1	--	ND	Pass

ND = Not Detected (&lt; Detection Limit)

Main test instruments used for this method:

Instrument	Manufactory	Model / Type
ICP-OES	PerkinElmer	Avio 550 Max

2.Test specification : Total Cadmium ----California Proposition 65

Test method : US EPA 3052:1996 and US EPA 6010D:2018

Requirement : California Proposition 65

Test Product No.	Testing element	Cd	Conclusion
	Detection Limit[mg/kg]	10.0	
	Limit [mg/kg]	100	
1-1	--	ND	Pass

ND = Not Detected (&lt; Detection Limit)

Main test instruments used for this method:

Instrument	Manufactory	Model / Type
ICP-OES	PerkinElmer	Avio 550 Max

3.Test specification : Phthalates ----California Proposition 65

Test method : CPSC-CH-C1001-09.4  
Standard Operating Procedure for Determination of Phthalates

Requirement : California Proposition 65

Test Product No.	CAS No.	Detection	Limit	1-1
Dibutyl phthalate (DBP)	84-74-2	0.005%	0.1%	ND
Butyl benzyl phthalate (BBP)	85-68-7	0.005%	0.1%	ND
Di-2-ethylhexyl phthalate (DEHP)	117-81-7	0.005%	0.1%	ND
Di- <i>iso</i> -decyl phthalate (DIDP)	26761-40-0/ 68515-49-1	0.005%	0.1%	ND
Di- <i>n</i> -hexyl phthalate(DnHP)	84-75-3	0.005%	0.1%	ND
Di- <i>iso</i> -nonyl phthalate (DINP)	28553-12-0/ 68515-48-0	0.005%	0.1%	ND
Conclusion				Pass

ND = Not Detected ( < Detection Limit)

Main test instruments used for this method:

Instrument	Manufactory	Model / Type
GC-MS	Agilent Technologies	GC (7890)-MS (5975C)

4. US FDA 21 CFR 177.2600: Rubber articles intended for repeated use

Product name:1-1.White silica gel					
Parameter	Test Specification	Unit	Limit	Detection Limit	Result
Distilled water reflux	First time: 7 hours	mg/inch <sup>2</sup>	20	1.0	ND
	Second time:2 hours	mg/inch <sup>2</sup>	1	1.0	ND
n - Hexane reflux	First time: 7 hours	mg/inch <sup>2</sup>	175	1.0	14.6
	Second time:2 hours	mg/inch <sup>2</sup>	4	1.0	ND
Conclusion	--				Pass

Note:

- 1) mg/inch<sup>2</sup>= mg per square inch
- 2) ND=Not Detected(<Detection Limit)

Sample photo(s), see annex 1

---End---

**ANNEX 1**

Sample photo(s), consists of 1 page



TS2022101104

SILICONE SPATULA/SINK STRAINER