



TEST REPORT

Test information

Applicant	:	Ningbo Home-Dollar Imp.& Exp.Corp.
Address	:	69 Guangyuan Road, Jiangbei District, Ningbo,China.
Sample Description	:	KITCHEN TOOLS.
Style #	:	G25992.
Country of origin	:	China.
Export to	:	USA.
Buyer	:	REGENT PRODUCTS CORP.
Receiving Date	:	July 02, 2022.
Test period	:	July 02, 2022.~July 07, 2022.
Amended date	:	July 08, 2022.
Test Requested	:	Tests requested in accordance to client requirement.

<u>TEST ITEMS</u>	<u>CONCLUSION</u>
Maximum extractable fraction – US FDA 21 CFR 177.1500	PASS

Signed for and on behalf of
RTS TEST CO., LTD.(Zhejiang)

BINBIN ZOU

Approved signatory



Zhejiang RTS Test Co., LTD.

Phone: +86(0)579-85640080

Email: ruiyi-8@zi-rts.com

<http://www.irtslab.com>

浙江省义乌市稠江街道英才创业园B区7幢2-4层,
2-4f, Building 7, Block B, Ying cai Business Park,
Choujiang Street, Yiwu, Zhejiang.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request. Attention is drawn to the limitation of liability ,indemnification and jurisdictional policies defined therein .The results shown in this Test report refer only to the sample(s) tested unless otherwise stated This test report shall not be reproduced ,except in full, without written approval of the Company. If in doubt, please write an email. * This item is beyond CNAS permitting capacity list and proceed by outsourcing labs.

Sample image:



Finished product image[△]:



Note: [△]=Not a test sample,The customer declares that the same parts of the batch and the test sample are made from the same batch of raw materials,RTS does not do authenticity audit.



Test result:

A. *Maximum extractable fraction – US FDA 21 CFR 177.1500:

Test method: With reference to FDA 21 CFR 177.1500.

Test Number	Item/ component description(s)	Material (claimed by the client)		
A1	Black nylon spoon	Nylon PA66		
Simulant Used	Time	Temp	Test result A1	Maximum Permissible Limit
Maximum extractable fraction in water, w/w %	8h	reflux temperature	<0.10	1.5

Note:

1)%(w/w) = percentage of weight by weight.

----- End of Report -----