



Report No.: RTS220714P2053FD

Date : 2022-07-18

Page 1 of 4

TEST REPORT

Test information

Applicant	: NINGBO SHIMAOTONG INTERNATIONAL CO.,LTD.
Address	: Room 1203, Building 004, 495 Jiangdong North Road, Yinzhou District, Ningbo City, Zhejiang Province.
Sample Description	: plastic scoop.
PO#	: Not provided.
Style #	: Not provided.
Country of origin	: China.
Export to	: Not provided.
Buyer	: Not provided.
Receiving Date	: July 14, 2022.
Test period	: July 14, 2022.~July 18, 2022.
Test Requested	: Tests requested in accordance to client requirement.

<u>TEST ITEMS</u>	<u>CONCLUSION</u>
Total Lead(Pb) Content - California Proposition 65- Superior Court of California-County of Alameda Case No. RG10-545680/ RG-10-545687.	PASS
Extractable fraction in n-hexane – US FDA 21 CFR 177.1520	PASS

Signed for and on behalf of
RTS TEST CO., LTD. (Zhejiang)

BINBIN ZOU

Approved signatory



Scan to follow us



Scan for authenticity

Zhejiang RTS Test Co., LTD.

Phone: +86(0)579-85640080

Email: ruiyi-@zi-rt.com

<http://www.irtslab.com>

浙江省义乌市稠江街道英才创业园B区7幢2-4层,
2-4f, Building 7, Block B, Ying cai Business Park,
Choujiang Street, Yiwu, Zhejiang.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request. Attention is drawn to the limitation of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test report refer only to the sample(s) tested unless otherwise stated. This test report shall not be reproduced, except in full, without written approval of the Company. If in doubt, please write an email. * This item is beyond CNAS permitting capacity list and proceed by outsourcing labs.

Sample image:



**Test result:****A. Total Lead(Pb) content:** (Unit: mg/kg)

California Proposition 65- Superior Court of California- County of Alameda Case No.RG 10-545680/ RG-10-545687.

Test method: As per Metal - CPSC-CH-E1001.08.3; Nonmetal - CPSC-CH-E1002.08.3; Surface coating -

CPSC-CH-E1003.09.1, Was analyzed by flame atomic absorption spectrometry (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Test Number	Item/ component description(s)
A1	PP scoop (red & black)

Test item	Test Number	MDL	Test Result	Maximum permissible limit	Conclusion
Lead (Pb)	A1▲	5	N.D.	200	PASS

Note:

- 1) MDL=Method Detection Limit.
- 2) N.D. = not detected, less than MDL.
- 3) Paints and surface coatings shall not exceed 90 ppm (0.009%) total lead content.
- 4) Substrates shall not exceed 200 ppm (0.020%) total lead content.
- 5)“▲” = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.

Remark:

Zhejiang RTS Test Co.,Ltd. is the US (CPSC) Accredited Third Party Testing Laboratory, [LAB ID: 1422](#), Shall refer to:

<https://www.cpsc.gov/cgi-bin/LabSearch/ViewDetail.aspx?ReqId=7%2bFdY2oZNSUVU5mvl6jQA%3d%3d&LabId=CJaa18d5DKIPqgie8zcyw%3d%3d>

Zhejiang RTS Test Co., LTD.

Phone: +86(0)579-85640080

Email: ruiyi-8@zi-rt.com

<http://www.irtslab.com>

浙江省义乌市稠江街道英才创业园B区7幢2-4层.
2-4/f, Building 7, Block B, Ying cai Business Park,
Choujiang Street, Yiwu, Zhejiang.

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request. Attention is drawn to the limitation of liability ,indemnification and jurisdictional policies defined therein .The results shown in this Test report refer only to the sample(s) tested unless otherwise stated This test report shall not be reproduced ,except in full, without written approval of the Company. If in doubt, please write an email.



B.*Extractable fraction in n-hexane – US FDA 21 CFR 177.1520:(Unit: w/w %)

Test method: With reference to US FDA 21 CFR 177.1520.

Test Number	Item/ component description(s)	Material (claimed by the client)
A2	White PP scoop	PP

Simulant Used	Time	Temp	Detection limit	Test result A2	Maximum permissible Limit
Extractable fraction in n-hexane at reflux temperature , w/w %	2h	reflux temperature	0.5	0.59	6.4

Note:

- 1)N.D= Not detected, less than Detection limit.
- 2)%(w/w) = percentage of weight by weight.
- 3) Maximum permissible Limit is reference to 21 CFR 177.1520(c) 1.1a.

----- End of Report -----