



Applicant: NINGBO REAL RAISING IMPORT & EXPORT CO., LTD.
Rm 1502, China Base Building No.666 Tiantong South Rd,
Ningbo,China
Contact(s): /

Overall Rating:

Data	<input type="checkbox"/>
Satisfactory	<input checked="" type="checkbox"/>
Unsatisfactory	<input type="checkbox"/>
Others, See Detail Enclosed	<input type="checkbox"/>

Sample Information

 	Client:	/
	Supplier:	/
	Supplier No.:	/
	Factory:	/
	Model:	FS2208146
	Description:	SPIDER WEB BASKET W/LEGS PLASTIC 3 AST
	Sample Amount:	/
	Sample Status:	Good
	Bulk finish status:	/
	While inspection:	/
	Country of Origin:	China
	Destination:	U.S.A
	Received Date:	07. 02, 2023
	Testing Period:	07. 02, 2023 to 20. 02, 2023
Remark:	/	

PREPARED BY: _____

Jerry

AUDITED BY: _____

Erick

APPROVED BY: _____

lm

CCMA/Ningbo Helmsman Quality Testing Services Co., Ltd.
ADDRESS: 818 Jinyuan Road, Jinchou District, Ningbo City, Zhejiang, China
Tel: 86-574-83020752 Postcode: 315105 Email: Report Query (testing_quality@hqts.cn)

The results of this report are only indicative or representative of the quality or characteristics of the test sample unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. You have 15 days from date of issuance of this report to notify us of any material error or omission caused by our negligence, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission.



Testing Report

Report No.: HN20230451

Date: 2023-02-20

Page 2 of 4

Testing Summary of Tested Component on Submitted Sample:

Density at 23°C - Food and Drug Administration (FDA) Regulations 21 CFR 177.1520	PASS
Melting Point - Food and Drug Administration (FDA) Regulations 21 CFR 177.1520	PASS
Extractable fraction in n-hexane at reflux temperature Extractable fraction in n-hexane at reflux temperature - Food and Drug Administration (FDA) Regulations 21 CFR 177.1520	PASS
Soluble fraction in xylene at 25°C-Food and Drug Administration (FDA) Regulations 21 CFR 177.1520	PASS

***** To be Continued

COMPANY: Ningbo Helmsman Quality Testing Services Co., Ltd.

ADDRESS: 818 Jinyuan Road, Yinzhou District, Ningbo City, Zhejiang, China

Tel: 86-574-83028482 Postcode: 315105 Email: Report Query (testing_quality@hqts.cn)

The results set forth in this report are only indicative or representative of the quality or characteristics of the test sample unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. You have 15 days from date of issuance of this report to notify us of any material error or omission caused by our negligence, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission.

Test Result(s):**Test Sample Description:**

Sample No.	Client Claimed Material	Sample Description
01	PP	Green plastic basin
02	PP	Black plastic basin
03	PP	Orange plastic basin

A. Test Results for Homo-polypropylene**Test Method:** With reference to US FDA 21 CFR 177.1520**Test result:**

Test Items	Unit	Limit	Result(s)	Conclusion(s)
			01	
1. Density at 23°C	g / cm ³	0.880 – 0.913	0.904	PASS
2. Melting Point	°C	160 – 180	165.0	PASS
3. Extractable fraction in n-hexane at reflux temperature	w/w %	< 6.4	0.6	PASS
4. Soluble fraction in xylene at 25°C	w/w %	< 9.8	0.4	PASS

Test Items	Unit	Limit	Result(s)	Conclusion(s)
			02	
1. Density at 23°C	g / cm ³	0.880 – 0.913	0.909	PASS
2. Melting Point	°C	160 – 180	165.7	PASS
3. Extractable fraction in n-hexane at reflux temperature	w/w %	< 6.4	1.4	PASS
4. Soluble fraction in xylene at 25°C	w/w %	< 9.8	0.8	PASS

Test Items	Unit	Limit	Result(s)	Conclusion(s)
			03	
1. Density at 23°C	g / cm ³	0.880 – 0.913	0.906	PASS
2. Melting Point	°C	160 – 180	166.4	PASS
3. Extractable fraction in n-hexane at reflux temperature	w/w %	< 6.4	1.0	PASS
4. Soluble fraction in xylene at 25°C	w/w %	< 9.8	1.3	PASS

Note: 1. "<" = less than.

COMPANY: Ningbo Helmsman Quality Testing Services Co., Ltd.

ADDRESS: 818 Jinyuan Road, Yinzhou District, Ningbo City, Zhejiang, China

Tel: 86-574-83028482 Postcode: 315105 Email: Report Query (testing_quality@hqts.cn)

The results set forth in this report are only indicative or representative of the quality or characteristics of the test sample unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. You have 15 days from date of issuance of this report to notify us of any material error or omission caused by our negligence, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission.

Photo Attachment



*******End of Report*******

COMPANY: Ningbo Helmsman Quality Testing Services Co., Ltd.

ADDRESS: 818 Jinyuan Road, Yinzhou District, Ningbo City, Zhejiang, China

Tel: 86-574-83028482 Postcode: 315105 Email: Report Query (testing_quality@hqts.cn)

The results set forth in this report are only indicative or representative of the quality or characteristics of the test sample unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. You have 15 days from date of issuance of this report to notify us of any material error or omission caused by our negligence, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission.