

## Test Report

Testing institute : Product Technology Service (Ningbo) Co., Ltd.  
5,6,7F, 59#, Huayu Road, Yinzhou District, Ningbo, Zhejiang

Applicant : NINGBO YUBO IMPORT AND EXPORT CO.,LTD.  
NO.150, HUIJIANG ROAD YINZHOU DISTRICT NINGBO(1704-A CHENGNAN  
BUSINESS BUILDING)

Product name : ICE CUBE

Model No. : G89360

Sample Description : /

Material : /

Sample receive date : Mar.08,2023

Completes date : Mar.13,2023

Test specification(s)	Conclusion
1. US FDA 21 CFR 177.2600: Rubber articles intended for repeated use(e)&(f)	
(e)Rubber articles intended for repeated use in contact with aqueous food;	Pass
(f)Rubber articles intended for repeated use in contact with fatty foods.	Pass
2.Total Lead ----California Proposition 65	Pass
3.Total Cadmium ----California Proposition 65	Pass
4.Phtalates ----California Proposition 65	Pass

Signed for and on behalf of  
Product Technology Service (Ningbo) Co., Ltd.

*Meng Wei*

Authorizer: Meng Wei



The test results exclusively refer to the samples examined. The test report is only used for scientific research, teaching or internal quality control. This report shall not be reproduced except in full without written approval and does not authorize the use of Product Technology Service (Ningbo) Co., Ltd. label. The report is invalid without signature and seal of Product Technology Service (Ningbo) Co., Ltd.

Product name

No.	Name	Part No.	Part Name
1	ICE CUBE	1-1	White TPR ice lattice
		1-2	White ice lattice+purple ice lattice+orange ice lattice (mixed-tested)

Remark: According to client's requirement, samples were mixed-tested.

1.US FDA 21 CFR 177.2600: Rubber articles intended for repeated use

Product name:1-1.White TPR ice lattice					
Parameter	Test Specification	Unit	Limit	Detection Limit	Result
Distilled water reflux	First time: 7 hours	mg/inch <sup>2</sup>	20	1.0	ND
	Second time:2 hours	mg/inch <sup>2</sup>	1	1.0	ND
n - Hexane reflux	First time: 7 hours	mg/inch <sup>2</sup>	175	1.0	151.4
	Second time:2 hours	mg/inch <sup>2</sup>	4	1.0	2.9
Conclusion	--				Pass

Note:

- 1) mg/inch<sup>2</sup>= mg per square inch
- 2) ND=Not Detected(<Detection Limit)

2.Test specification : Total Lead ----California Proposition 65

Test method : CPSC-CH-E1002-08.3

Requirement : California Proposition 65

Test Product No.	Testing element	Pb	Conclusion
	Detection Limit[mg/kg]	10.0	
	Customer's requirement	100	
1-2	--	ND	Pass

ND = Not Detected ( < Detection Limit)

Main test instruments used for this method:

Instrument	Manufactory	Model / Type
ICP-OES	PerkinElmer	Avio 550 Max

3.Test specification : Total Cadmium ----California Proposition 65

Test method : US EPA 3052:1996 and US EPA 6010D:2018

Requirement : California Proposition 65

Test Product No.	Testing element	Cd	Conclusion
	Detection Limit[mg/kg]	10.0	
	Customer's requirement	100	
1-2	--	ND	Pass

ND = Not Detected ( < Detection Limit)

Main test instruments used for this method:

Instrument	Manufactory	Model / Type
ICP-OES	PerkinElmer	Avio 550 Max

4.Test specification : Phthalates ----California Proposition 65

Test method : CPSC-CH-C1001-09.4  
Standard Operating Procedure for Determination of Phthalates

Requirement : California Proposition 65

Test Product No.	CAS No.	Detection Limit	Customer's requirement	1-2
Dibutyl phthalate (DBP)	84-74-2	0.005%	0.1%	ND
Butyl benzyl phthalate (BBP)	85-68-7	0.005%	0.1%	ND
Di-2-ethylhexyl phthalate (DEHP)	117-81-7	0.005%	0.1%	ND
Di-iso-decyl phthalate (DIDP)	26761-40-0/ 68515-49-1	0.005%	0.1%	ND
Di-n-hexyl phthalate(DnHP)	84-75-3	0.005%	0.1%	ND
Di-iso-nonyl phthalate (DINP)	28553-12-0/ 68515-48-0	0.005%	0.1%	ND
Conclusion				Pass

ND = Not Detected ( < Detection Limit)

Main test instruments used for this method:

Instrument	Manufactory	Model / Type
GC-MS	Agilent Technologies	GC (7890)-MS (5975C)

Sample photo(s), see annex 1

---End---

**ANNEX 1**

Sample photo(s), consists of 1 page



ICE CUBE