

# TEST REPORT

**APPLICANT**

: REGENT PRODUCTS CORP.

**ADDRESS**: 8999 PALMER STREET, RIVER GROVE, IL 60171-1926  
U.S.A**SAMPLE DESCRIPTION**: HALLOWEEN RAT WITH  
BLACK/GREY ASSORTMENT/CHAIN  
W/HAND OR SKULL DANGLE  
ASSORTMENT/B/O SKELETON  
ANIMAL ASSORTMENT/CHAIN WITH SEVERED HAND OR  
FOOT  
ASSORTMENT/PLASTIC CHAIN WITH NECK & HAND  
CUFF /12.5"  
SKELETON ASSORTMENT/SET OF 1  
PACK/2 PACK HALLOWEEN PVC  
HANGING BAT  
ASSORTMENT/PLASTIC ANIMAL  
SKELETON  
ASSORTMENT/HALLOWEEN YARD  
STAKE BEWARE WITH WOOD LOOK  
ASSORTMENT/PLASTIC SKELETON  
ANIMAL DINOSAUR/PUMPKIN WITH FALL FLOWER  
DÉCOR  
ASSORTMENT/LARGE PUMPKIN  
WITH SUNFLOWER  
ASSORTMENT/16" HARVEST  
FLORAL PICK ASSORTMENT/SET OF  
2 PACK HARVEST BOWS  
ASSORTMENT/11" CHRISTMAS PINE  
PVC TREE WITH BURLAP WRAPPED  
ASSORTMENT/SET OF 2 PACK  
CHRISTMAS PICKS WITH GLITTER ACCESSORIES  
ASSORTMENT /24"  
CHRISTMAS POINSETTIA PICK WITH ACCESSORIES  
ASSORTMENT/16"  
CHRISTMAS POINSETTIA HANGING  
DÉCOR ASSORTMENT

*Samples are obtained by express delivery, Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to [info.sh@eurofins.com](mailto:info.sh@eurofins.com) and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to [china.complaint@eurofins.com](mailto:china.complaint@eurofins.com) and referring to this report number.*



**ITEM NO.** : G89307/ G89412/ G89554(766977)/ G89596/ G897050/  
 G89725/ G89793(790663)/ G89827/ G89838/ G89745/  
 G94011/ G94012/ G94014/ G94015/ G91445/ G91448/  
 G91500/ G91506

**BUYER** : 99 CENTS ONLY STORE

**COUNTRY OF DESTINATION** : U.S.A.

**SAMPLE RECEIVED DATE** : 07-Mar-2023

**SAMPLE RESUBMISSION DATE** : 20-Mar-2023

**TURN AROUND TIME** : 07-Mar-2023 to 22-Mar-2023

The following test item(s) was/were performed on submitted sample(s) and/or component(s) confirmed by applicant

TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Tracking Label Assessment	US CPSIA, Section 103	See Test Result
Total Lead Content in Paint / Surface Coating	US CPSIA, Section 101	Pass
Total Lead Content	US California Proposition 65	Pass
Total Cadmium Content	US California Proposition 65	Pass
Phthalates Content	US California Proposition 65	Pass
Phthalates Content	CPSC 16 CFR part 1307	Pass
Phthalates Content	US CPSIA, Section 108	Pass
Formaldehyde Content	ISO 14184-1:2011	See Test Result
Phthalates Content	US California Proposition 65 (Halloween)	Pass

**Eurofins (Shanghai) contact information**

**Customer service:** [Nicola.Yang@cpt.eurofinscn.com](mailto:Nicola.Yang@cpt.eurofinscn.com)/ 36202999

**Sales specialist:** [RoyFeng@eurofins.com](mailto:RoyFeng@eurofins.com)/ +86 216 1819 181

\*\*\*\*\* FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) \*\*\*\*\*

Signed for and on behalf of  
Eurofins Product Testing Service (Shanghai) Co., Ltd




Joyce Liu  
Operation Director

*Samples are obtained by express delivery, Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to [info.sh@eurofins.com](mailto:info.sh@eurofins.com) and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to [china.complaint@eurofins.com](mailto:china.complaint@eurofins.com) and referring to this report number.*

**SAMPLE PHOTO(S)**



**A**



**B**



**C**



**D**



**E**




**F**


**EFSH23030447-CG-01**

\*\*\*TO BE CONTINUED\*\*\*

**SAMPLE PHOTO(S)**



**G**



**H**



**I**



**J**



**K**




**L**

**EFSH23030447-CG-01**

\*\*\*TO BE CONTINUED\*\*\*

**SAMPLE PHOTO(S)**



**EFSH23030447-CG-01**

\*\*\*TO BE CONTINUED\*\*\*

## COMPONENT LIST

Component No.	Component	Sample No.
1	White foam with red glitter	C,D
2	Silver glitter on plastic	B,D
3	Gold glitter on plastic	H
4	Red coating on metal	A
5	Red coating on plastic	C
6	Grey coating on plastic	I,J,O
7	White coating on plastic	K,L
8	Red coating on plastic	K,L,P
9	Silver coating on plastic	L,M,N
10	Black coating on plastic	O
11	Brown coating on plastic	Q
12	White fabric with silver plastic threads	B
13	Yellow/green plastic	A,B
14	Beige yellow plastic excluding coating	Q
15	Dark green plastic threads	A,B,C
16	Green plastic threads	A,B
17	Green plastic (leaves)	A,B,E,G
18	Transparent plastic	B
19	Dark green plastic	B
20	Grey plastic excluding glitter	B
21	Brown plastic	C,E,G
22	Yellow plastic excluding glitter	D
23	Transparent green plastic	E
24	Light brown plastic	F,G
25	Red brown plastic	F
26	Transparent plastic	H
27	Grey white plastic	I,J
28	Transparent red plastic	I
29	Light green plastic excluding glitter	H
30	Black plastic excluding coating	K,L,M,N
31	Black plastic	O
32	White plastic	O
33	Beige plastic	O
34	Transparent red plastic	O
35	White plastic	P
36	Orange/gold soft plastic film	H
37	Red soft plastic film (fruit)	A,C
38	Orange soft plastic film	F,G
39	Grey soft plastic	P
40	Black soft plastic	R
41	Silver soft plastic threads (rope)	B
42	Black elastic rubber of black elastic band	I,R
43	White material	C
44	Transparent yellow dry glue	B
45	White foam with multi-color printing	F,G
46	Orange/yellow fabric	E,G,H
47	Orange/brown fabric	E
48	Red/orange fabric	F
49	Multi-color fabric	G
50	Green/brown fabric	H

\*\*\*TO BE CONTINUED\*\*\*

<b>Component No.</b>	<b>Component</b>	<b>Sample No.</b>
51	Red flocking fabric	A
52	Green fabric	A,B,C,D
53	Brown mesh fabric	C
54	Brown fabric	C
55	Brown mesh fabric	E
56	Yellow fabric	F
57	Orange fabric	F
58	Red brown fiber	E,G
59	Black textile of black elastic band	I,R
60	Silver metal (rod)	A,B
61	Silver metal excluding coating	A
62	Silver metal	B
63	Silver metal (nail)	E
64	Silver metal (screw)	O

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Tracking Label Assessment

Test Request: As per Consumer Product Safety Improvement Act (CPSIA) 2008 section 103 tracking labels for children products

Labeling Content	Observation Result	Location	Conclusion
Name of Manufacturer/ Import / Private Labeler in the tracking label	Provide	Packaging	Pass
Location of production	Provide	Packaging	Pass
Date of production	Provide	Packaging	Pass
Cohort information (including the batch, run number, or other identifying characteristic)	Provide	Packaging	Pass
Name of Manufacturer/ Import / Private Labeler in the tracking label	Not Present	Product	See Remark
Location of production	Not Present	Product	See Remark
Date of production	Not Present	Product	See Remark
Cohort information (including the batch, run number, or other identifying characteristic)	Not Present	Product	See Remark

#### **Remark:**

There were no Name of Manufacturer/importer/Private Labeler in the tracking label and Location of production and Date of production and Cohort information (including the batch, runnumber, or other identifying characteristic) information present on product.

According to CPSC Document "Interpretation and Enforcement of Section 103(a) of the Consumer Product Safety Improvement Act", a manufacturer may choose to employ a code or numbering system provided the required information remains ascertainable by the consumer.

Each manufacturer is ultimately responsible for making a reasonable judgment about what information can be marked on their product and packaging, given the character and type of their product and packaging, and what required information can be ascertainable, given the character and type of their business.

The tracking label assessment was based on the submitted sample and the information provided by the applicant. There was no verification on the validity of such information.

\*\*\*TO BE CONTINUED\*\*\*



## TEST RESULT

### Total Lead Content in Paint / Surface Coating

Test Request: Total lead in paint/ similar surface coatings as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101  
 Test Method: CPSC-CH-E1003-09.1  
 The sample was acid digested, and total lead content was determined by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				1	2+3	4+5+6	7+8+9
Total Lead (Pb)	mg/kg	90	10	ND	ND	24	ND

Test Item(s)	Unit	Limit	MDL	Result
				10+11
Total Lead (Pb)	mg/kg	90	10	ND

**Remark:**

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Total Lead Content

Test Request: Total lead content as specified in US California Proposition 65.

Test Method: EPA 3050B:1996, EPA 3051A:2007, EPA 3052:1996, acid digestion/ microwave digestion method was used, analysis was performed by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				1	2+3	4+5+6	7+8+9
Lead (Pb)	mg/kg	90	10	ND	ND	24	ND

Test Item(s)	Unit	Limit	MDL	Result			
				10+11			
Lead (Pb)	mg/kg	90	10	ND			

Test Item(s)	Unit	Limit	MDL	Result			
				12	13	14+15+16	17+18+19
Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				20+21+22	23+24+25	26+27+28	29+30+31
Lead (Pb)	mg/kg	100	10	ND	13	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				32+33+34	35	36	37+38+39
Lead (Pb)	mg/kg	100	10	ND	ND	12	15

Test Item(s)	Unit	Limit	MDL	Result			
				40+41+42	43	44	45
Lead (Pb)	mg/kg	100	10	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result	
				60+61+62	63+64
Lead (Pb)	mg/kg	100	10	ND	ND

#### Remark:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

The limit(s) was/were referred from various court cases. Compliance with the above stated limit(s) does not show compliance with Proposition 65 or a guarantee against possible legal action but provides a relative level of assurance against potential lawsuits.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Total Cadmium Content

Test Request: Total cadmium content as specified in US California Proposition 65

Test Method: EPA 3050B:1996, EPA 3051A:2007, EPA 3052:1996, acid digestion/ microwave digestion method was used, analysis was performed by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result			
				1	2+3	4+5+6	7+8+9
Cadmium (Cd)	mg/kg	300	5	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				10+11	12	13	14+15+16
Cadmium (Cd)	mg/kg	300	5	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				17+18+19	20+21+22	23+24+25	26+27+28
Cadmium (Cd)	mg/kg	300	5	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				29+30+31	32+33+34	35	36
Cadmium (Cd)	mg/kg	300	5	ND	ND	ND	ND

Test Item(s)	Unit	Limit	MDL	Result			
				37+38+39	40+41+42	43	44
Cadmium (Cd)	mg/kg	300	5	ND	ND	19	ND

Test Item(s)	Unit	Limit	MDL	Result		
				45	60+61+62	63+64
Cadmium (Cd)	mg/kg	300	5	ND	ND	ND

#### Remark:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

The limit(s) was/were referred from various court cases. Compliance with the above stated limit(s) does not show compliance with Proposition 65 or a guarantee against possible legal action but provides a relative level of assurance against potential lawsuits.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Phthalates Content

Test Request: Phthalates Content as specified in US California Proposition 65

Test Method: EPA 3550C:2007, EPA 8270E:2018, solvent extraction and quantification by GC-MS.

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1	2+3	4+5+6	7+8+9
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					10+11	12	13
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	0.031
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					14	15	16
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	0.008
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	0.020	0.030
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	0.021	0.016
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					17+18+19	20+21+22	23+24+25	26+27+28
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	0.009	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	0.023	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					29+30+31	32+33+34	35	36
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					37+38+39	40+41+42	43	44
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	0.029
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result
					45
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND

**Remarks:**

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

The limit(s) was/were referred from various court cases.

Compliance with the above stated limit(s) does not show compliance with Proposition 65 or a guarantee against possible legal action but provides a relative level of assurance against potential lawsuits.

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Phthalates Content

Test Request: Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates as specified in CPSC 16 CFR part 1307.

Test Method: CPSC-CH-C1001-09.4

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1	2+3	4+5+6	7+8+9
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					10+11	12	13
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	0.031
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					14	15	16
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	0.021	0.016
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	0.020	0.030
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	0.008
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					17+18 +19	20+21 +22	23+24 +25	26+27 +28
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	0.023	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	0.009	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*



## TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					29+30+31	32+33+34	35	36
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					37+38+39	40+41+42	43	44
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	0.029
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result
					45
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND

**Remarks:**

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Phthalates Content

Test Request: Phthalates Content as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 108

Test Method: CPSC-CH-C1001-09.3

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1	2+3	4+5+6	7+8+9
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					10+11	12	13
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	0.031
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					14	15	16
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	0.008
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	0.020	0.030
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	0.021	0.016
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					17+18+19	20+21+22	23+24+25	26+27+28
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	0.009	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	0.023	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					29+30+31	32+33+34	35	36
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					37+38+39	40+41+42	43	44
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	0.029
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result
					45
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND
Diethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND
Diisodecylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND

**Remarks:**

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

MDL = method detection limit

ND = Not detected, less than MDL

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Formaldehyde Content

Test Method: ISO 14184-1:2011, free and hydrolized formaldehyde (water extraction method)

Test Item(s)	CAS No.	Unit	MDL	Result			
				12	46	47	48
Formaldehyde	50-00-0	mg/kg	16	ND	34	47	79

Test Item(s)	CAS No.	Unit	MDL	Result			
				49	50	51+52+53	54+55+56
Formaldehyde	50-00-0	mg/kg	16	ND	58	85	18

Test Item(s)	CAS No.	Unit	MDL	Result			
				57+58+59			
Formaldehyde	50-00-0	mg/kg	16	34			

#### Remarks:

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

“-” = Not regulated

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Phthalates Content

Test Request: Phthalates Content as specified in US California Proposition 65 (Halloween)

Test Method: EPA 3550C:2007, EPA 8270E:2018, solvent extraction and quantification by GC-MS.

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					1	2+3	4+5+6	7+8+9
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octyl phthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					10+11	12	13
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Di-n-octyl phthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	0.031
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result		
					14	15	16
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	0.008
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	0.020	0.030
Di-n-octyl phthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	0.021	0.016
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					17+18+19	20+21+22	23+24+25	26+27+28
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	0.009	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	0.023	ND
Di-n-octyl phthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*



## TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					29+30+31	32+33+34	35	36
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octyl phthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

Test Item(s)	CAS No.	Unit	Limit	MDL	Result			
					37+38+39	40+41+42	43	44
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND	ND
Di-n-octyl phthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND	0.029
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

Test Item(s)	CAS No.	Unit	Limit	MDL	Result
					45
Di-n-butyl phthalate (DBP)	84-74-2	%	0.1	0.005	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	0.1	0.005	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	0.1	0.005	ND
Di-n-octyl phthalate (DNOP)	117-84-0	%	0.1	0.005	ND
Diisononyl phthalate (DINP)	28553-12-0	%	0.1	0.005	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	0.1	0.005	ND
Dihexyl phthalate (DHP/DnHP)	84-75-3	%	0.1	0.005	ND

**Remarks:**

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

Compliance with the above stated limit(s) does not show compliance with Proposition 65 or a guarantee against possible legal action but provides a relative level of assurance against potential lawsuits.

Remark:

MDL = method detection limit

ND = Not detected, less than MDL

\*\*\*END OF THE REPORT\*\*\*