

Report No.: RTS230322X2178HLBG1 Date : 2023-04-08 Page 1 of 6

# **TEST REPORT**

Test information				
Applicant	:	Ningbo Home-Dollar Imp.& Exp.Corp.		
Address	:	69 Guangyuan Road, Jiangbei District, Ningbo,China.		
Sample Name	:	BLOOD FAKE RED/GLOW CREAM.		
PO#	:	Not provided.		
Style#	:	G89558T.		
Buyer	:	REGENT PRODUCTS CORP.		
Country of origin	:	China.		
Export To	:	USA.		
Receiving Date	:	March 22, 2023.		
Test period	:	March 22, 2023.∼April 08, 2023.		
Amended Date	:	April 04, 2023.		
Test Requested	:	Tests requested in accordance to client requirement.		

TEST ITEMS	CONCLUSION
Total Lead(Pb) content - CPSIA Section 101	PASS
Lead(Pb) in Paint and Other similar Surface coating - CPSIA Section 101 & 16 CFR Part 1303	PASS
Phthalates Content test- CPSC 16 CFR PART 1307	PASS
Determination of Amount of Net Chloroform Soluble Extractives – US FDA 21 CFR 177.1630	PASS



**Approved signatory** 

Zhejiang RTS Test Co., LTD.

Phone: +86(0)579-85640080 Email: ruiyi-8@zj-rts.com http://www.irtslab.com 排江省义与市翻江街道英才创业园 B 区 7 幢 2-4 层. 2-4/f, Building 7, Block B, Ying cai Business Park, Choujiang Street, Yiwu, Zhejiang.



Report No.: RTS230322X2178HLBG1 Date: 2023-04-08 Page 2 of 6

# Sample image:







Report No.: RTS230322X2178HLBG1 Date : 2023-04-08 Page 3 of 6

# **Test result:**

#### A1. Total Lead content: (Unit: mg/kg)

Section 101 of the Consumer Product Safety Improvement Act of 2008 (CPSIA) (pdf) (Public Law 110-314), as modified by H.R. 2715 (Public Law 112-28, August 12, 2011) and in section 2(q)(1) of the Federal Hazardous Substances Act (pdf), 15 U.S.C. § 1261(q)(1) (FHSA).

#### Test method:

Metal - CPSC-CH-E1001-08.3., Nonmetal - CPSC-CH-E1002-08.3.,

Was analyzed by flame atomic absorption spectrometry (AAS) or inductively coupled plasma spectrometer (ICP-OES).

Test Numb	Item/ component description(s)		
A1	Transparent plastic teeth		

Test item	Test Number	MDL	Test Result	Maximum permissible limit	Conclusion
Lead	A 1	E	ND	100	DACC
(Pb)	A1	) 3	N.D.	100	PASS

#### Note:

- 1) MDL=Method Detection Limit.
- 2) N.D. = not detected, less than MDL.
- 3) Any substrate material, that is not more than 100ppm lead by weight.
- 4)" A" = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.

# Remark:



Report No.: RTS230322X2178HLBG1 Date: 2023-04-08 Page 4 of 6

# A2. Lead in paint/similar surface coating material: (Unit: mg/kg)

Section 101 of the Consumer Product Safety Improvement Act of 2008 (CPSIA) (pdf) (Public Law 110-314), as modified by H.R. 2715 (Public Law 112-28, August 12, 2011) and in 16 CFR part 1303.

# Test method:

Surface coating- CPSC-CH-E1003-09.1, Was analyzed by flame atomic absorption spectrometry (AAS) or inductively coupled plasma spectrometer (ICP-OES).

Test Number	Item/ component description(s)		
A2	Red fake blood		

Test item	Test Number	MDL	Test Result	Maximum permissible limit	Conclusion
Lead	A2	5	N.D.	90	PASS
(Pb)	A2	3	N.D.	90	FA33

#### Note:

- 1) MDL=Method Detection Limit.
- 2) N.D. = not detected, less than MDL.
- 3) Any surface coating, that is not more than 90ppm lead by weight.
- 4)" A" = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.



Report No.: RTS230322X2178HLBG1 Date : 2023-04-08 Page 5 of 6

# B. Phthalates Content Test: (Unit: mg/kg)

Consumer Product Safety Commission (CPSC)16 CFR PART 1307 Prohibited children's toys and child care articles shall not contain more than 0.1% of any of the specified phthalates.

Test method: With reference to CPSC-CH-C1001-09.4, was analyzed by Gas Chromatograph-Mass Spectrometer (GC-MS).

Test Number	Item/ component description(s)		
A1	Transparent plastic teeth		
A2	Red fake blood		

Took Hom/o)	CAS No.	Results		MDL	Limit value
Test Item(s)	CAS NO.	A1	A2	WIDL	Lillit value
Dibutyl Phthalate(DBP)	84-74-2	N.D.	N.D.	50	1000
Benzylbutyl Phthalate(BBP)	85-68-7	N.D.	N.D.	50	1000
Bis-(2-ethylhexyl)Phthalate(DEHP)	117-81-7	N.D.	N.D.	50	1000
Di-iso-nonyl Phthalate(DINP)	28553-12-0	N.D.	N.D.	50	1000
Diisobutyl phthalate (DIBP)	84-69-5	N.D.	N.D.	50	1000
Dipentyl phthalate (DPENP)	131-18-0	N.D.	N.D.	50	1000
di-n-Hexyl phthalate (DHEXP)	84-75-3	N.D.	N.D.	50	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	N.D.	N.D.	50	1000
Conclusion	-	PASS	PASS	-	-

#### Note:

2-4/f, Building 7, Block B, Ying cai Business Park, Choujiang Street, Yiwu, Zhejiang.

<sup>1)</sup> N.D. = not detected, less than MDL.

<sup>2)</sup> MDL = Method Detection Limit.

<sup>3)&</sup>quot;▲" = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.



Report No.: RTS230322X2178HLBG1 Date: 2023-04-08 Page 6 of 6

# C.\* Determination of Amount of Net Chloroform Soluble Extractives - US FDA 21 CFR 177.1630:

Test method: With reference to US FDA 21 CFR 177.1630.

Test Number	Item/ component description(s)	Material (claimed by the client)
A1	Transparent plastic teeth	PET

Extractants	Test Condition	Detection limit	Test result(mg/in²)	Permissible Limit
Extractants	rest Condition	(mg/in²)	A1	(mg/in²)
Distilled Water	120°F for 24 hours	0.1	N.D.	0.5
N-Heptane	120°F for 24 hours	0.1	0.24	0.5
50% Ethyl alcohol	120°F for 24 hours	0.1	N.D.	0.5

#### Note:

- 1) N.D. = Not detected, less than Detection limit .
- 2) mg/in<sup>2</sup> = milligram per square inch.
- 3) \*=Denotes as the result(s) of chloroform-soluble extractives.
- 4) #=Denotes as the result(s) of chloroform-soluble extractives was (were) adjusted to correct for zinc as zinc oleate and reported as net value(s).

End	d of Repor	t
-----	------------	---