

Report No.: RTS230316X1669HL Date: 2023-03-22 Page 1 of 5

TEST REPORT

		Test information
Applicant	:	Ningbo Home-Dollar Imp.& Exp.Corp.
Address	:	69 Guangyuan Road, Jiangbei District, Ningbo,China.
Sample Name	:	CHRISTMAS PLATE.
PO#	:	Not provided.
Style#	:	G91433.
Buyer	:	REGENT PRODUCTS CORP.
Country of origin	:	China.
Export To	:	USA.
Receiving Date	:	March 16, 2023.
Test period	:	March 16, 2023.∼March 22, 2023.
Test Requested	:	Tests requested in accordance to client requirement.

TEST ITEMS	CONCLUSION
Total Lead(Pb) Content - California Proposition 65- Superior Court of California- County of Santa Clara Case No. 112CV231165.	PASS
Total Cadmium(Cd) Content - California Proposition 65- Superior Court of California- County of Alameda Case No. RG 10-514803.	PASS
Phthalates Content test- Client's requirement	PASS
Total Residual styrene monomer – FDA 21 CFR 177.1640	PASS

Signed for and on behalf of RTS TEST CO., LTD. Zhellang) **BINBIN ZOU**

Approved signatory

Zhejiang RTS Test Co., LTD.

Phone: +86(U)579-85640080 Email: ruiyi-8@zj-rts.com http://www.irtslab.com 附在含义与市朝江街道英才创业园 B 区 7 幢 2-4 层. 2-4/f, Building 7, Block B, Ying cai Business Park, Choujiang Street, Yiwu, Zhejiang.



Report No.: RTS230316X1669HL Date: 2023-03-22 Page 2 of 5

Sample image:







Report No.: RTS230316X1669HL Date: 2023-03-22 Page 3 of 5

Test result:

A. Total Lead(Pb) content: (Unit: mg/kg)

California Proposition 65- Superior Court of California- County of Santa Clara Case No. 112CV231165.

Test method: As per Metal - CPSC-CH-E1001.08.3; Nonmetal - CPSC-CH-E1002.08.3; Surface coating - CPSC-CH-E1003.09.1, Was analyzed by flame atomic absorption spectrometry (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Test Number	Item/ component description(s)
A1	Transparent PS plate

Test item	Test Number	MDL	Test Result	Maximum permissible limit	Conclusion
Lead	A1	Б	N.D.	100	PASS
(Pb)	Ai	5	N.D.	100	PASS

Note:

- 1) MDL=Method Detection Limit.
- 2) N.D. = not detected, less than MDL.
- 3) Products shall not exceed 100 ppm (0.01 %) total lead content.
- 4)" A" = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.

Remark:



Report No.: RTS230316X1669HL Date: 2023-03-22 Page 4 of 5

B. Total Cadmium(Cd) content: (Unit: mg/kg)

California Proposition 65- Superior Court of California- County of Alameda Case No. RG 10-514803

Test method: RTS-ZY-008 As per Metal - CPSC-CH-E1001-08.3; Nonmetal - CPSC-CH-E1002-08.3; Surface coating - CPSC-CH-E1003-09.1, Was analyzed by flame atomic absorption spectrometry(AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Test Number	Item/ component description(S)
A1	Transparent PS plate

Test item	Test Number	MDL	Test Result	Maximum permissible limit	Conclusion
Cadmium	۸1	5	N.D.	300	PASS
(Cd)	A1	3	IN.D.	300	rass

Note:

- 1) MDL=Method Detection Limit.
- 2) N.D. = not detected, less than MDL.
- 3) Product shall not exceed 300 ppm (0.030%) total cadmium content.
- 4)"▲" = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.



Report No.: RTS230316X1669HL Date: 2023-03-22 Page 5 of 5

C.Phthalates Content Test: (Unit: mg/kg)

Test method: With reference to CPSC-CH-C1001-09.4, was analyzed by Gas Chromatograph-Mass Spectrometer (GC-MS).

Test Number	Item/ component description(s)
A1	Transparent PS plate

Test Item(s)	CAS No.	Results A1	MDL	Client's Limit
Dibutyl Phthalate(DBP)	84-74-2	N.D.	50	1000
Benzylbutyl Phthalate(BBP)	85-68-7	N.D.	50	1000
Bis-(2-ethylhexyl)Phthalate(DEHP)	117-81-7	N.D.	50	1000
Di-iso-nonyl Phthalate(DINP)	28553-12-0	N.D.	50	1000
Di-iso-decylphthalate(DIDP)	26761-40-0	N.D.	50	1000
Di-n-hexyl phthalate(DNHP)	84-75-3	N.D.	50	1000
Conclusion	-	PASS	-	-

Note:

- 1) N.D. = not detected, less than MDL.
- 2) MDL = Method Detection Limit.
- 3)" A" = This data is obtained from composite testing on more than one materials or shapes, it is possible that result obtained from individual testing on any one of the materials or shapes is substantially higher. Please be cautious when using this data for compliance evaluation.

D. *Total Residual styrene monomer - FDA 21 CFR 177.1640:

Test method: With reference to FDA 21 CFR 177.1640.

Test Number	Item/ component description(s)	Material (claimed by the client)
A1	Transparent PS plate	PS

Test item	Detection limit	Test result A1	Maximum permissible Limit	
Total Residual styrene monomer w/w %	0.001	0.088	0.5	

Note:

- 1) N.D. = not detected, less than Detection limit.
- 2) (w/w) %= percentage of weight by weight.

	End	of Re	port	
--	-----	-------	------	--